

Shape Resonances in superconducting gaps in a 2DEG at oxide-oxide interface

A Bianconi¹, **D Innocenti**¹, **A Valletta**², **A Perali**³

¹RICMASS, Rome International Center for Materials Science Superstripes,
Via dei Sabelli 119A, 00185 Rome, Italy

²Department of Physics, Institute for Microelectronics and Microsystems, IMM CNR,
Via del Fosso del Cavaliere 100, 00133 Roma, Italy

³Physics Unit, School of Pharmacy, University of Camerino, 62032 Camerino, Italy

E-mail: antonio.bianconi@ricmass.eu;

Abstract. In multiband superconductivity, the case where the single electron hopping between different Fermi surface spots of different symmetry is forbidden by selection rules is recently attracting a large interest. The focus is addressed to superconductivity made of multiple condensates with different symmetry where the chemical potential crosses a 2.5 Lifshitz transition. This can now be investigated experimentally by fine-tuning of the chemical potential in the range of tens meV around a band edge using gate voltage control. We discuss here the case of a superconducting two-dimensional electron gas (2DEG), at the interface between two insulating oxides confined within a slab of 5 nanometers thickness, where the electronic structure is made of subbands generated by quantum size effects. We obtain shape resonances in the superconducting gaps, characteristic gaps to T_c ratios and the BCS-BEC crossover in the upper subband for different pairing strength in the shallow Fermi surface, pointing toward the best configurations for enhanced superconductivity in 2DEG.


1. Introduction

There is growing agreement that advances in quantitative protocols for material design of high temperature superconductors should be based on the control of a) lattice parameters, b) defects distribution and c) tuning of the chemical potential, in heterostructures at atomic limit [1-13]. Since 1993 [1] it has been proposed that it is possible to increase the superconducting critical temperature by selecting an optimal geometrical architecture of composite materials made of atomic layers (or wires or stripes) intercalated by nanoscale spacers. The interest is focusing on tuning the chemical potential near a band edge where “shape resonances” in superconducting gaps appear in multi-condensates superconductivity [1-13].

The “shape resonance” is a type of Fano resonance in the configuration interaction between open and closed scattering channels, well known in atomic and nuclear physics [14-17] which occurs in the pairing processes in multi-condensates superconductors by the tuning the chemical potential near a band edge, as it was first recognized by Blatt [18,19]. It was first shown in 1996 [3-5] that the “shape resonance” gives the maximum of the critical temperature where the chemical potential is tuned above the band edge so that the Fermi energy in the small Fermi surface is of the order of one-two times the the energy scale of the pairing interaction. Therefore the shape resonance in the superconducting gaps



gives a maximum T_c where the interacting Fermi liquid in the upper band is in the crossover regime from a Bose-like to a Fermi-like behavior [20-25,10].




Superconductivity in thin metallic films with a thickness at atomic limit has been shown to persist to thicknesses much below the superconducting coherence length and even down to a single layer films [26-32]. Interestingly, in low dimensional superconductors, the superconducting coherence length (ξ) or the magnetic penetration depth (λ) do not define the critical length scale for the destruction of the superconducting state.

Layered complex metal oxides made of different modules provide systems with unique electronic, magnetic, ferroelectric and superconducting properties due to lattice heterogeneity, valence fluctuations, lattice misfit strain, photoinduced effects, complex phase separation high temperature superconductivity [33-43].

At interfaces between complex oxides, electronic systems with unusual electronic properties can be generated [44,45]. Evidence of a two-dimensional electron gas (2DEG) at interfaces between two oxides LaAlO_3 and SrTiO_3 has been reported by several groups [46-49]. This 2DEG provides a superconducting layer that is a realization of a two-dimensional superconductor in a thin slab of finite thickness with superconducting transition temperature of 200 milli-Kelvin [45-48].

Maevasana et al. [49] have found a 2DEG with electron density as large as $8 \times 10^{13} \text{ cm}^{-2}$ formed at the bare SrTiO_3 surface of a cleaved crystal and its density can be controlled through exposure of the surface to intense ultraviolet light. The results show that the chemical potential can be tuned above the bottom of the second sub-band due to quantum size effects. These findings have been confirmed by a

systematic study using angle-resolved photoemission spectroscopy (ARPES) providing new insights into the electronic structure of the 2DEG [50]. They shed light on previous observations in SrTiO₃-based heterostructures and suggest that different forms of electron confinement at the surface of SrTiO₃ lead to essentially the same 2DEG. There is therefore compelling evidence for an exotic 2DEG that forms at oxide interfaces based on SrTiO₃, but its precise nature remains elusive.



Recently Biscaras et al. [51] and Bert et al. [52] have investigated the superconducting phase by controlling the chemical potential in the 2DEG by electrostatic back gate voltage. Biscaras et al. have shown that the superconducting 2DEG is confined into a slab of about 5 nanometers at the LaTiO₃ side of the (Mott insulator)/SrTiO₃ (band insulator) interface forming subbands due to quantum size effect like it is shown in Figure 1.

Figure 1 shows the 2D metallic slab hosting the 2DEG of thickness L . The total density of states $N(E)$ for the two dimensional subbands made of sharp steps at the band edge of each subband controlled by quantum size effects. By using the gate voltage the chemical potential is tuned to the bottom of the upper subband at about 100 meV above the bottom of the lowest subband. The subbands show a dispersion in the k_x (k_x, k_y) plane. The electronic occupation of the upper subband controls the superconducting properties via the small Fermi surface produced by electrons in the upper n -th subband.

The chemical potential in the 2DEG is tuned by the gate voltage to the point where it crosses the bottom of the upper n -th subband, i.e., a 2.5 Lifshitz transition for appearing of a new Fermi surface spot near $k_x(k_x, k_y)=0$. Changing the gate voltage field the superconducting transition temperature shows a sharp increase as soon as the small Fermi surface spot due to finite Fermi energy in the n -th subband appears. The critical temperature increases to a maximum value followed by a smooth decrease as a function of the gate voltage [51]. Bert et al. [52] has reported magnetization and susceptibility measurements made by using a scanning SQUID (Superconducting Quantum Interference Device) [52], with a 3 μm diameter pick-up loop and a concentric field coil for applying a local AC magnetic field. They have been able to measure the superfluid density of the superconducting state and to obtain the curve of the critical temperature as a function of the superfluid density shown in Figure 2.

2. Results and discussion

We have calculated the superconducting gaps and the critical temperature in a metallic slab of 5 nanometers using our theoretical approach described in our previous papers [10,11] which is able to describe the superconducting phase near a band edge in a multiband system. The electrons are confined by a very high barrier of 5 eV within the slab and the Schrödinger equation is solved to get the wavefunction of electrons in different Fermi surface spots. The electronic structure of the normal phase is made of multiple subbands as shown in Figure 1. The chemical potential is tuned around the bottom of the 6th subband in an energy range of meV. The BCS multi gaps equations for multiband superconductivity are calculated together with the density equation. The chemical potential μ is tuned around the bottom of the upper subband E of n -th subband ($n=6$). In the band edge region of the n -subband there is a strong renormalization of the chemical potential going from the normal to the superconducting phase which should be included in any theoretical approach.

The superconducting gaps in the subbands of the 2DEG in the slab of 5 nanometer thickness at the $\text{LaTiO}_3/\text{SrTiO}_3$ interface are shown in Figure 3. The chemical potential is tuned by changing the charge density from the bottom of the first subband. At each 2.5 Lifshitz transition for appearing of a new Fermi surface spot at the band edge of the n -th subband a new condensate is formed and its gap energy increases from zero up to reach a maximum. The superconducting gaps in the $n-1$ subbands with $m < n$ are very similar. The figure shows three cases a) intraband coupling in the m -th subbands ($m < n$) in the very weak coupling range $c_{mm}=0.1$. b) intraband coupling in the n -th subband in the strong coupling range $c_{nn}=0.5$, with an interband $c_{ni}=0.1$ c) the intraband coupling is the same as in panel b but now there is a strong exchange pair transfer term $c_{ni}=0.5$


The position of the chemical potential is measured by the Lifshitz parameter $z=(\mu-E_{n,L})/\omega_0$ where $E_{n,L}$ is the energy of the bottom of the n -th electronic subband and ω_0 is the energy cut off of the pairing interaction. When the Lifshitz parameter z is in the range $-1 < z < 0$ the n -th subband is empty in the normal state but a Bose-like condensate is formed there by bosons created by the strong pairing interaction in the upper n -th subband and the pair transfer from the lower m -th subbands. For $0 < z < 1$ the Fermi liquid in the n -th subband forms a small Fermi surface where the Fermi energy is smaller than the pairing interaction energy. Therefore the electrons in the n -th subband are in the anti-adiabatic regime where polaron formation is expected and in the superconducting phase bipolarons could form and condense. In this regime the wave-vector of electrons in the n -th Fermi surface k_{Fn} could be smaller than the inverse of the superconducting coherence length $1/\xi_0$ where $(k_{Fn} \xi_0) < 2\pi$ and T_c versus superfluid density follows the Uemura plot. In cuprates this regime is called the “underdoped regime” or “pseudogap regime”. In the range $1 < z < 2$ the superconducting phase is in a crossover regime approaching the BCS regime for $z > 2$.

We report in Figure 3 the calculation of the superconducting gaps in the upper subband n -th and in the $(n-1)$ -th subband and the critical temperature. We assume a weak coupling regime in the lower subbands taking for the intraband coupling strength the value $c=0.1$.

The green region in Figure 3 corresponds to values of the Lifshitz parameter z , ($-1 < z < 0$) therefore the n -th subband is empty with no associated Fermi surface in the normal phase. On the other hand, the effective pairing interaction centered around the chemical potential is already able to make available for pair formation states in the n -th subband, thanks to its extension in energy of the order of ω_0 induced by the retardation effects of the electron-phonon coupling. In this situation the condensate component of the n -th subband starts to form well before the appearing of a new Fermi surface in the normal state. This condensate has a Bose-like character, being the underlying Fermi surface not yet formed and its coherence factor $v(k)^2$ quite delocalized as a function k , implying Cooper pairs with a local character in real space.

The yellow region in Figure 3 corresponds to positive values of the Lifshitz parameter z , $0 < z < 1$: the chemical potential is above the bottom of the n -th subband and a new (small) Fermi surface

appears in the electronic spectrum. The superconducting gap is of the order of the energy difference $\mu - E_{n,L}$ (which is the Fermi energy for the n -th subband) and the system is in the crossover regime between BCS and BEC.



The precise extension of the crossover region depends from the couplings regime, being wider in the Lifshitz parameter z for stronger couplings, leading to larger gap values in the n -th subband, as in panel (c) of Figure 3. This crossover regime is highly non trivial, because the full superconducting system has a condensate which is a coherent mixture of BCS-like (forming in $(n-1)$ -th subband) and Bose-like pairs (in the n -th subband) and the local Fermi energy $E_{F_{n,L}} = \mu - E_{n,L}$ is less or of the same order of the energy cutoff of the interaction ω_0 , which leads to non adiabatic effects in the superconducting properties in which the electron-phonon coupling play a role. For this reason this yellow region in Figure 3 can be also addressed as a crossover-antiadiabatic regime.

The blue region in Figure 3, with $1 < z < 1.5$, corresponds to a more conventional crossover to BCS regime for multi-band superconductivity. The frontier between the crossover regime and the BCS regime has the optimal characteristics for the amplification of superconductivity in 2DEG. Anti-adiabatic effects, which in general suppress superconductivity for conventional electron-phonon couplings, start to be negligible, while superconducting fluctuations can be lowered in their detrimental effects by the coexistence of small and large well formed Fermi surface in the spectrum, with the large Cooper pairs forming in the large Fermi surface being able to transfer their large superconducting stiffness to the smaller Cooper pairs of the small Fermi surface by means of the interband Josephson-like exchange coupling. Finally, for $z > 2$, the 2DEG superconducting system is in a BCS regime of conventional multi-band superconductivity.




Figure 5: The gap ratio in the n -th (red dots) and m -th subbands (black dots) versus the critical temperature tuning the chemical potential in the 3 considered cases of figures 3 and 4. The figures show three cases a) intraband and interband coupling in all subbands are the weak coupling range 0.1; b) the intraband coupling in the upper n -th subband in the strong coupling range 0.5; c) intraband coupling in the n -th ($n=6$) and m -th subbands are like in panel (b) but the exchange pair transfer term is much larger, $c_{nm}=0.5$.

In Figure 5 we report the variation of the gap ratio $2\Delta/T_c$ as a function of the superconducting critical temperature. We show that where the intraband pairing terms are weak as well as the interband pair transfer interaction in panel (a) the gap ratio $2\Delta/T_c$ is similar in different bands, and it is close to the BCS standard value 3.5 for a single large Fermi surface. In panel 2 the BCS ratio in the upper subband, which is in the strong electron-phonon coupling limit, is much larger than 3.5 while for the other subbands, which are in the weak coupling limit $c_{nm}=0.1$, is much smaller. Panel (c) shows that by increasing the interband pair transfer term $c_{nm}=0.5$ the difference of the gap ratio in different bands decreases and it approaches again the BCS ratio 3.5.

In Figure 6 we plot the critical temperature as a function of the superfluid density for the three cases we have investigated. The results clearly show that in the mixed Bose-Fermi regime the critical temperature increases as a function superfluid density like in the Uemura plot and by reaching the Fermi regime and the multiband BCS condensation regime the critical temperature saturates and decreases increasing the superfluid density for all investigated cases as in the low superfluid density regime in Figure 2. Further work is needed to clarify the strength of the pair transfer term between different electronic components at the Fermi level in this 2DEG.




Figure 6: The critical temperature versus the superfluid density in the new appearing subband in the log-log plot. The figure shows three cases (panel a) intraband coupling in the n -th subband in the very weak coupling range 0.1; (panel b) intraband coupling in the n -th subband in the strong coupling range 0.5, (panel c) where the intraband coupling parameters are like in the panel (b) but with a much stronger exchange pair transfer term $c_{nm}=0.5$.

3. Conclusions

In conclusion one of our most important results: the superconducting shape resonance leading to the optimal amplification of the gap energies and of the critical temperature is located in the range $1 < z < 2$, and the critical temperature and the gaps in the lower m subbands have minima in the range $-1 < z < 0$. It is indeed necessary for the system to go over the Lifshitz critical point to stabilize at the same time lattice and superconducting fluctuations. Optimal superconductivity therefore needs two formed and underlying Fermi surfaces: one large with weak coupling and another smaller one with strong coupling, with the local Fermi level close to the band bottom of the upper band, at an energy distance of the order of the characteristic energy scale of the pairing interaction, together with the interband exchange Josephson-like coupling allowing for (constructive) interference effects between the condensate of the bands.

References

- [1] Bianconi A 1994 On the possibility of new high T_c superconductors by producing metal heterostructures as in the cuprate perovskites *Sol. State Commun.* **89** 933
- [2] Bianconi A, Saini NL, Rossetti T, Lanzara A, Perali A, Missori M 1996 Stripe structure in the CuO_2 plane of perovskite superconductors *Phys. Rev. B* **54** 12018
- [3] Perali A, Bianconi A, Lanzara A, Saini NL 1996 The gap amplification at a shape resonance in a superlattice of quantum stripes: A mechanism for high T_c *Sol. State Commun.* **100**

- [4] Bianconi A, Valletta A, Perali A and Saini NL 1997 High T_c superconductivity in a superlattice of quantum stripes *Solid State Commun.* **102** 369
- [5] Valletta A, Bianconi A, Perali A, Saini NL 1997 Electronic and superconducting properties of a superlattice of quantum stripes at the atomic limit *Zeitschrift für Physik B Condensed Matter* **104** 707
- [6] Bianconi A, Di Castro D, Agrestini S, Campi G, Saini N L, Saccone A, De Negri S, Giovannini M 2001 A superconductor made by a metal heterostructure at the atomic limit tuned at the 'shape resonance': MgB_2 *Journal of Physics: Condensed Matter* **13** 7383-7390
- [7] Bussmann-Holder A, Bianconi A 2003 Raising the diboride superconductor transition temperature using quantum interference effects *Physical Review B* **67** 132509
- [8] Bianconi A, Agrestini S, Bussmann-Holder A 2004 The T_c amplification by shape resonance in doped MgB_2 *Journal of Superconductivity* **17** 205
- [9] Bianconi A 2005 Feshbach Shape Resonance in Multiband Superconductivity in Heterostructures *J. Supercond. Novel Magn.* **18** 625
- [10] Innocenti D, Poccia N, Ricci A, Valletta A, Caprara S, Perali A, Bianconi A 2010 Resonant and crossover phenomena in a multiband superconductor: Tuning the chemical potential near a band edge *Physical Review B* **82** 184528
- [11] Innocenti D, Valletta A, Bianconi A 2011 Shape resonance at a Lifshitz transition for high temperature superconductivity in multiband superconductors *Journal of Superconductivity and Novel Magnetism* **24** 1137
- [12] Bussmann-Holder A, Keller H, Khasanov R, Simon A, Bianconi A, Bishop AR 2011 Isotope and interband effects in a multi-band model of superconductivity *New Journal of Physics* **13** 093009
- [13] Perali A, Innocenti D, Valletta A, Bianconi A 2012 Anomalous isotope effect near a 2.5 Lifshitz transition in a multi-band multi-condensate superconductor made of a superlattice of stripes *Superconductor Science and Technology* **25** 124002
- [14] Fano U 1935 Sullo spettro di assorbimento dei gas nobili presso il limite dello spettro d'arco *Il Nuovo Cimento (1924-1942)* **12** 154
- [15] Fano U 1961 Effects of Configuration Interaction on Intensities and Phase Shifts *Phys. Rev.* **124** 1866 URL
- [16] Bianconi A 2003 Ugo Fano and shape resonances *AIP Conference Proceedings* **652**,13-18.
- [17] Vittorini-Orgeas A, Bianconi A 2009 "From Majorana Theory of Atomic Autoionization to Feshbach Resonances in High Temperature Superconductors *Supercond Nov Magn* **52** 215
- [18] Blatt J, Thompson C 1963 Shape Resonances in Superconducting Thin Films *Physical Review Letters* **10** 332
- [19] Blatt JM 1964 *Theory of Superconductivity* Academic Press New York (for shape resonances see pag. 362 and 215)
- [20] Leggett A J 1966 *Prog. Theor. Phys.* **36** 901; Leggett AJ 1966 *Prog. Theor. Phys.* **36** 931
- [22] Leggett A J 1980 *Modern Trends in the Theory of Condensed Matter*, edited by A. Pekalski and R. Przystawa, Lecture Notes in Physics, Springer-Verlag, Berlin, vol 115 p 13
- [23] Sá de Melo CAR, Randeria M, Engelbrecht JR 1993 Crossover from BCS to Bose superconductivity: Transition temperature and time-dependent Ginzburg-Landau theory *Phys. Rev. Lett.* **71** 3202
- [24] Shanenko A A, Croitoru M D, Vagov A V, Axt V M, Perali A, and Peeters F M 2012 Atypical BCS-BEC crossover induced by quantum-size effects *Phys. Rev. A* **86** 033612
- [25] de Llano M, Tolmachev VV 2003 Multiple phases in a new statistical boson-fermion model of superconductivity *Physica A: Statistical Mechanics and its Applications* **317** 546 ; Malik G P, Chávez I, de Llano M 2013 *Journal of Modern Physics* **4** 474
- [26] Bao XY, Zhang YF, Wang Y, Jia JF, Xue QK, Xie XC, Zhao Z X, 2005 Quantum size effects on the perpendicular upper critical field in ultrathin lead films *Physical Review Letters* **95** 247005
- [27] Qin S, Kim J, Niu Q, Shih CK 2009 Superconductivity at the Two-Dimensional limit *Science* **324** 1314

- [28] Bose S, Garcia Garcia A M, Ugeda M M, Urbina J D, Michaelis C H, Brihuega I, Kern K 2010 *Nat. Mat.* **9** 550
- [29] Zhang T, Cheng P, Li W-J, Sun Y-J, Wang G, Zhu X.-G, He K, Wang L, Ma X, Chen X, Wang Y, Liu Y, Lin H-Q, Jia J-F, Xue Q-K 2010 Superconductivity in one-atomic-layer metal films grown on Si(111) *Nature Physics* **6** 104
- [30] Shanenko AA, Croitoru MD, and Peeters FM 2006 *EPL* **76** 498
- [31] Shanenko AA, Croitoru M D, Zgirski M, Peeters F M, Arutyunov K 2006 *Phys. Rev. B* **74** 052502
- [32] García-García AM, Urbina JD, Yuzbashyan EA, Richter K, Altshuler BL 2011 BCS superconductivity in metallic nanograins: Finite-size corrections, low-energy excitations, and robustness of shell effects *Phys. Rev. B* **83**, 014510
- [33] Campi G, Ricci A, Poccia N, Barba L, Arrighetti G, Burghammer M, Caporale A S, Bianconi A 2013 Scanning micro-x-ray diffraction unveils the distribution of oxygen chain nanoscale puddles in YBa₂Cu₃O_{6.33} *Physical Review B* **87** 014517
- [34] Ricci A, Poccia N, Campi G, Coneri F, Caporale AS, Innocenti D, Burghammer M, Zimmermann M, Bianconi A 2013 Multiscale distribution of oxygen puddles in 1/8 doped YBa₂Cu₃O_{6.67} *Scientific Reports* **3** 2383
- [35] Poccia N, Ricci A, Campi G, Fratini M, Puri A, Di Gioacchino D, Marcelli A, Reynolds M, Burghammer M, Saini N L, Aeppli G, Bianconi A 2012 Optimum inhomogeneity of local lattice distortions in La₂CuO_{4+y} *Proceedings of the National Academy of Sciences* **109** 15685
- [36] Poccia N, Fratini M, Ricci A, Campi G, Barba L, Vittorini-Orgeas A, Bianconi G, Aeppli G, Bianconi A 2011 Evolution and control of oxygen order in a cuprate superconductor *Nat Mater* **10** 733
- [37] Takahashi M, Maeda T, Uemura K, Yao J, Tokuda Y, Yoko T, Kaji H, Marcelli A 2007 Photoinduced Formation of Wrinkled Microstructures with Long-Range Order in Thin Oxide Films *Advanced Materials* **19**
- [38] Campi G, Di Castro D, Bianconi G, Agrestini S, Saini NL, Oyanagi H, Bianconi A 2002 Photo-Induced phase transition to a striped polaron crystal in cuprates *Phase Transitions* **75** 927
- [39] Di Castro D, Bianconi G, Colapietro M, Pifferi A, Saini NL, Agrestini S, Bianconi A 2000 Evidence for the strain critical point in high T_c superconductors *The European Physical Journal B - Condensed Matter and Complex Systems* **18** 617
- [40] Bianconi A, Saini N L, Agrestini S, Di Castro D, Bianconi G 2000 The strain quantum critical point for superstripes in the phase diagram of all cuprate perovskites *International Journal of Modern Physics B* **14** 3342
- [41] Bianconi A, Di Castro D, Bianconi G, Pifferi A, Saini N. L, Chou FC, Johnston DC, Colapietro M 2000 Coexistence of stripes and superconductivity: T_c amplification in a superlattice of superconducting stripes *Physica C: Superconductivity* **341** 1719
- [42] Bianconi A, Missori M, Oyanagi H, Yamaguchi H, Nishiara Y, Della Longa S 1995 The measurement of the polaron size in the metallic phase of cuprate superconductors *EPL (Europhysics Letters)* **31** 411
- [43] Müller KA and Bednorz J G 1987 A Road Towards High-Temperature Superconductivity *Physica Scripta* **1987** 23
- [44] Mannhart J, Schlom D G 2010 Oxide Interfaces-An Opportunity for Electronics *Science* **327** 1607
- [45] Hwang H Y, Iwasa Y, Kawasaki M, Keimer B, Nagaosa N and Tokura Y 2012 Emergent phenomena at oxide interfaces *Nature Materials* **11** 103
- [46] Reyren N, Thiel S, Caviglia AD, Kourkoutis LF, Hammerl G, Richter C, et al. 2007 Superconducting Interfaces Between Insulating Oxides *Science* **317** 1196
- [47] Biscaras J, Bergeal N, Kushwaha A, Wolf T, Rastogi A, Budhani R C, Lesueur J 2010 Two-dimensional superconductivity at a Mott insulator/band insulator interface LaTiO₃/SrTiO₃ *Nature Communications* **1** 89

- [48] Bert J A, Kalisky B, Bell C, Kim M, Hikita Y, Hwang HY, Moler K A 2011 Direct imaging of the coexistence of ferromagnetism and superconductivity at the LaAlO₃/SrTiO₃ interface *Nature Phys* **7** 767
- [49] Basletic M, Maurice J-L, Carretero C, Herranz G, Copie O, Bibes M, Jacquet E, Bouzouane K, Fusil S, Barthelemy A 2008 Mapping the spatial distribution of charge carriers in LaAlO₃/SrTiO₃ heterostructures *Nature Materials* **7** 621
- [49] Caviglia A D, Gariglio S, Reyren N, Jaccard D, Schneider T, Gabay M, Thiel S, Hammerl G, Mannhart J, Triscone J -M 2008 Electric field control of the LaAlO₃/SrTiO₃ interface ground state *Nature* **456** 624
- [50] Meevasana W, King P D C, He R H, Mo S K, Hashimoto M, Tamai A, Songsirittigul P, Baumberger F and Shen Z X 2011 Creation and control of a two-dimensional electron liquid at the bare SrTiO₃ surface *Nature Materials* **10** 114
- [51] Santander-Syro AF, Copie O, Kondo T, Fortuna F, Pailhès S, Weht R, Qiu X G, Bertran F, Nicolaou A, Taleb-Ibrahimi A, et al, 2011 *Nature* **469** 189
- [52] Biscaras J, Bergeal N, Hurand S, Grossetête C, Rastogi A, Budhani RC, et al. 2012 Two-Dimensional Superconducting Phase in LaTiO₃/SrTiO₃ Heterostructures Induced by High-Mobility Carrier Doping *Phys Rev Lett* **108** 247004
- [53] Bert JA, Nowack KC, Kalisky B, Noad H, Kirtley JR, Bell C, et al. 2012 Gate-tuned superfluid density at the superconducting LaAlO₃/SrTiO₃ interface *Physical Review* **B** 86 060503